

#### LASER INTERFEROMETER GRAVITATIONAL WAVE OBSERVATORY

**SPECIFICATION** 

E1000075 -V1

Drawing No Vers.

Sheet 1 of 2

# **Mirror Specifications**

APPROVALS	DATE	RE V	DCN NO.	BY	CHECK	DCC	DATE
AUTHOR: L. BARSOTTI	3-5-10						
CHECKED:							
APPROVED: D. SIGG							
DCC RELEASE							

### **1** Description

0.5" Ø Flat/flat mirror @ 1064nm

## 2 Material

Corning HPFS 7980 (high purity fused silica, UV grade) Grade 0A (Low inclusion class: <0.3 mm<sup>2</sup> cross section, 0.1 mm max. size; Homogeneity < 1ppm)

## 3 Dimensions

.5"Ø +.000/-.005" X .125" ± .020" tk., flat/flat

## 4 Wedge

<60 arc seconds

## 5 Surface Roughness

#### Side 1

Super polish Surface Roughness: <1Å RMS in CA Surface Quality: 10-5 **Side 2** Commercial Polish Surface Roughness: <5Å RMS in CA Surface Quality: 40-20

## 6 Surface Figure

Side 1 Flat <  $\lambda$ /10 at 632.8 over central 80% Side 2 Flat <  $\lambda$ /4 at 632.8 over central 80%



# LIGO

# **SPECIFICATION**

E1000075 -V1

Drawing No Vers.

Sheet 2 of 2

# **Mirror Specifications**

## 7 Coating

Wavelength: 1064nm Angle of incidence: 0°- 45° Side 1 R > 99.95% @ 1064nm and AOI 0°- 45°, both s and p pol Side 2 AR coating, R<1% @ 1064nm and AOI 0°- 45°, both s and p pol

## Coating vendor to provide:

1. Two spectrophotometer graphs of the reflectance and transmittance of the HR coatings; one covering the spectrum from 530nm to 1200nm; the other, with increased sensitivity, showing wavelengths from 900nm to 1100nm

2. Spectrophotometer graphs of the reflectance of the AR coating taken as cited above.